

TECHNICAL DATASHEET



SOPLUTEC UV

Description

SOPLUTEC UV is a watertight breathable membrane composed of a non-woven polypropene with a UV resistant coating on the exterior side.

It is applied behind the exterior cladding as insulation protection in an exterior cladding system on framing with open joints \leq 30 mm and a total open joint area \leq 40 % of the total surface of the cladding.

In the longitudinal direction, the overlap is provided with a double self-adhesive strip assembly for efficient installation.

Characteristics

| Composition | Standard | Unit | Value | Tolerance |
|--|-----------------------------------|--------------------------------|---|----------------|
| Composition | | THE RELIES | non-woven polypropene with UV resistant coating | |
| Mass | | g/m² | 160 | |
| Finish | | | the exterior side is provided with an imprint | |
| Technical characteristics | | | | |
| Thickness | EN 1849-2 | mm | 0,50 | |
| Tensile force L B | EN 12311-1 | N/50 mm | 210 205 | -40/+30 ±30 |
| Elongation at max. tensile force L B | EN 12311-1 | % | 55 70 | ±15 -25/+15 |
| Resistance to tearing (nail shank) $\ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \$ | EN 12310-1 | N | 200 225 | ±60 ±15 |
| Water vapour diffusion-equivalent | EN 1931 | m | 0,14 | -0,01/+0,04 |
| Dimensional stability | EN 1107-1 | % | ±1,5 | |
| Resistance to air penetration | EN 12114 | m³/ (m².h.50 Pa) | 0,004 | |
| Durability to water penetration after artificial ageing | EN 1297 / EN 1296 / EN 1928 | 5000 h UV / 90 days / 70 °C | W1 | |
| Tensile force after artificial ageing L T | EN 1297 / EN 1296 / EN 12311-1 | N/50 mm | 190 180 | -60/+30 ±30 |
| Elongation at max. tensile force after artificial ageing L / T | EN 1297 / EN 1296 / EN 12311-1 | % | 50 / 40 | ±15 |
| Application temperature | 110000 | °C | -40/+100 | |
| Reaction to fire | EN 13501-1 | Class | Е | |
| Packing | | | | |
| Dimensions of the roll | EN 1848-1 | m | ≥ 50 x 1,5 | |
| Mass/roll | | kg | ± 12 | |
| Rolls/pallet | | | 20 | |

NPD = performance not determined

Store the rolls horizontal in a dry place protected from direct sunlight.

Installation

SOPLUTEC UV is installed with the print on the outside behind the vertical wooden or metal frame supporting structure of the cladding. It can be temporarily secured with nails or staples.

The longitudinal overlaps are sealed with the integrated double self-adhesive strip. The vertical overlaps are sealed with PAVAFIX tape or PAVABOND sealant.

After installation it must be completely covered to avoid damage.

Always consult the local regulations and contact the manufacturer for technical questions.

SOPREMA

TDS-NE-PROFR0007.d/EN

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

Contact: www.soprema.com



TECHNICAL DATASHEET



Special indications

Hygiene, Health and Environment

The product does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.

Quality-, Environment- and Safety Management SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety. For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with EN ISO 9001 and EN ISO 14001.



TDS-NE-PROFR0007.d/EN

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.